

## SPECIFICATIONS

Commercial	6082 - Obsolete
------------	-----------------

### Characteristic Properties:

Very good corrosion resistance. Very good weldability (lowered strength values in the weld zone). Good machinability. Good cold formability in T4 temper after a stabilizing heat treatment. Heat treatable medium high strength construction. Alloy with a strength somewhat higher than 6061. Medium high fatigue strength. Not suitable for complex sections.

## CHEMICAL COMPOSITION

BS L111(1971)  
Alloy L111

Element	% Present
Silicon (Si)	0.7 - 1.3
Magnesium (Mg)	0.5 - 1.2
Manganese (Mn)	0.4 - 1
Iron (Fe)	0.5 max
Chromium (Cr)	0.25 max
Titanium (Ti)	0.2 max
Zinc (Zn)	0.2 max
Copper (Cu)	0.1 max
Nickel (Ni)	0.1 max
Tin (Sn)	0.05 max
Lead (Pb)	0.05 max
Aluminium (Al)	Balance

## TEMPER TYPES

The most common temper for L111-6082 aluminium are:

- T4 - Solution heat treated and naturally aged to a substantially stable condition
- T5 - Cooled from an elevated temperature shaping process and artificially aged
- T6 - Solution heat treated and artificially aged
- T6511 - Solution heat treated and stress-relieved by stretching then artificially aged with minor straightening after aging

## SUPPLIED FORMS

L111-6082 aluminium is supplied in Bar and Extruded Sections.

- Bar
- Extrusions

## GENERIC PHYSICAL PROPERTIES

Property	Value
Density	2710 g/cm <sup>3</sup>
Melting Point	650 °C
Thermal Expansion	23.10 x10 <sup>-6</sup> /K
Modulus of Elasticity	70000 GPa
Thermal Conductivity	167-216 W/m.K

## MECHANICAL PROPERTIES

The Mechanical Properties values shown apply to material in the T6511 temper.

In the table, 'Dimension' means diameter or minor sectional dimension.

Dimension (mm)	Proof Strength	Tensile Strength	Elongation
Up to & incl. 20	255 Min	295 Min	7% Min
Over 20 up to & incl. 150	270 Min	310 Min	8% Min
Over 150 up to & incl. 200	240 Min	280 Min	5% Min

## CONTACT

Address: (incorporated in the USA)  
Tel: +44 (0)1371 811 642  
Email: info@aerometalsalliance.com

## REVISION HISTORY

Datasheet Updated 14 January 2019

## DISCLAIMER

This Data is indicative only and as such is not to be relied upon in place of the full specification. In particular, mechanical property requirements vary widely with temper, product and product dimensions. All information is based on our present knowledge and is given in good faith. No liability will be accepted by the Company in respect of any action taken by any third party in reliance thereon.

Please note that the 'Datasheet Update' date shown above is no guarantee of accuracy or whether the datasheet is up to date.

The information provided in this datasheet has been drawn from various recognised sources, including EN Standards, recognised industry references (printed & online) and manufacturers' data. No guarantee is given that the information is from the latest issue of those sources or about the accuracy of those sources.

Material supplied by the Company may vary significantly from this data, but will conform to all relevant and applicable standards.

As the products detailed may be used for a wide variety of purposes and as the Company has no control over their use; the Company specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by the Company to any third party is given for that party's assistance only and without liability on the part of the Company. All transactions are subject to the Company's current Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available on request.